



Specification Selector

Hot Dipped Galvanized Steel*

Service Environment	Specification					
	No.	Materials	Dry Film Thickness	No.	Materials	Dry Film Thickness
Internal Dry <i>Galvanized Steel</i>	Z1	Macropoxy™ L574 Acrolon™ 7300	25 50	Z2	Macropoxy™ K267	75
Internal Wet or External <i>Galvanized Steel</i>	Z3	Macropoxy™ K267 Acrolon™ 7300	100 50	Z4	Macropoxy™ K267 Macropoxy™ K267	75 75
Immersed in: Salt Water or Fresh Water** Buried in: Soil / Concrete <i>Galvanized Steel</i>				Z6	Macropoxy™ L574 Macropoxy™ L524 Macropoxy™ L524	25 125 125



Sherwin-Williams Specification No.



Substrate

* These specifications are to be used on HRS Steel that has been hot dipped galvanized

For CRS steel that is then galvanized, normally referred to as Galvatite that is typically used as purlins or on the underside of decking, please contact the Technical Enquiries Customer Support Team.

** Maximum Temperature 40°C

For Durability (Life to First Major Maintenance), see individual specification sheets.

If fire protection is required, please consult Sherwin-Williams Technical Enquiries Customer Support Team. (01204 556 457)

For maintenance and/or alternative substrate specifications, please contact Sherwin-Williams Technical Enquiries Customer Support Team.

The information detailed in this specification selector is liable to modification from time to time in the light of experience and of normal product development, and before using, customers are advised to check with Sherwin-Williams, quoting the reference number, to ensure that they possess the latest issue.

This Specification is specifically subject to the disclaimer which can be found at <http://protectiveemea.sherwin-williams.com/Home/Disclaimer>