



Tel: 01204 556 457
technicale@sherwin.com

Specification Sheet

ISO 12944-5 Ref: (C5D)

Steelwork

New Construction

Complies with ISO12944-5 : C5 Environment - Industrial areas with high humidity & aggressive atmosphere / Coastal areas with high salinity.

High Durability (15-25 years)

Surface Preparation:

Blast Clean to Sa2½ BS EN ISO 8501-1:2007 - Surface Profile between 50 - 75µm

Coat	Product	Product Type	Film Thickness µm		TSR (sqm/ltr)	Volume Solids %	Mixing Ratio	Pot Life 23°C
			Dry	Wet				
1st	Macropoxy™ 400	Zinc Phosphate Epoxy	125	179	5.6	70	7 : 1	1½ hrs
2nd	Macropoxy™ 400	Zinc Phosphate Epoxy	125	179	5.6	70	7 : 1	1½ hrs
3rd	Acrolon™ 7300 Gloss or Semi-Gloss	Acrylic Polyurethane	50	74	13.6	68	10 : 1	2 hrs

TSR = Theoretical Spread Rate

Product Code	Thinners	Touch Dry 15°C	Recoat 15°C	Touch Dry 23°C	Recoat 23°C	Sag Tolerance	Colour Range	Pack Size	Product Information
400	No.2 for Thinning - No.9/13 for Cleaning	1½ hrs	5 hrs	1 hr	3½ hrs	400µm d.f.t	Limited Inc, MIO	20 & 5 ltr	400 Data Sheets and Information
400	No.2 for Thinning - No.9/13 for Cleaning	1½ hrs	5 hrs	1 hr	3½ hrs	400µm d.f.t	Limited Inc, MIO	20 & 5 ltr	400 Data Sheets and Information
7300	No.15 for Thinning - No. 5 for Cleaning	4 hrs	9 hrs	1 hr	7 hrs	150µm d.f.t	Wide Range	20 & 5 ltr	7300 Data Sheets and Information

D.F.T = Dry Film Thickness

Notes:

- 1 Dry film thicknesses (d.f.t.) quoted are minimum nominal as defined by BS EN ISO 12944-5.
- 2 ISO12944 states that Durability is not a guarantee time. Durability should be considered as the coating design life, where regular minor maintenance should be scheduled to achieve the required life to first major maintenance.
- 3 Stripe coat all edges, welds and areas of difficult access, to ensure full film thickness.
- 4 Coated steelwork should be protected to prevent prolonged contact with water, e.g. ponding.
- 5 Subject to shade, multiple coats of the finish coat may be required to achieve the dft/ full colour obliteration.
- 6 All materials should be obtained from Sherwin-Williams and must be applied in accordance with our technical data sheets.
- 7 Certification available from Sherwin-Williams Technical Customer Support.
- 8 For fire protection systems, please contact Sherwin-Williams.
- 9 This specification is offered as guidance only. To ensure that the most appropriate materials are used, please contact Sherwin-Williams with the project details.